



a BN International Subsidiary

BN International s.r.o.,  
 Křenkova 283,  
 552 03 Česká Skalice,  
 Czech Republic  
 Tel. +420-491-401501  
 Fax +420-491-452005

## Technical Specification

BALACRYL 13 L				
Property				Test Method
Thickness		micron	330 ± 30	Tappi T411
Weight		g/m <sup>2</sup>	300 ± 20	Tappi T410
Tearing resistance	MD	mN	>3100	Tappi T414
	CD	mN	>3100	Tappi T414
Stiffness	MD	mN	>400	Tappi T494
	CD	mN	>200	Tappi T494
Tensile strenght	MD	N/inch	>200	Tappi T494
	CD	N/inch	>120	Tappi T494
Elongation	MD	%	< 12	Tappi T494
	CD	%	< 20	Tappi T494
Fold resistance	MD	DF	>12000	Tappi T423
	CD	DF	>6000	Tappi T423
Lightfastness			>6	EN ISO- 105-B 02
Temperature resistance		degr. Celsius	180	BN International
Changes	Date of issue		24.11.2020	
	Revision state		01	

date/signature  
 supplier

.....

date/signature  
 customer

.....



a BN International Subsidiary

BN International s.r.o.,  
 Křenkova 283,  
 552 03 Česká Skalice,  
 Czech Republic  
 Tel. +420-491-401501  
 Fax +420-491-452005

## Provisional Technical Specification

BALACRYL NG 15				
Property			Test Method	
Thickness		micron	375 ± 30	Tappi T411
Weight		g/m <sup>2</sup>	325 ± 20	Tappi T410
Tearing resistance	MD	mN	>3100	Tappi T414
	CD	mN	>3100	Tappi T414
Stiffness	MD	mN	>350	Tappi T494
	CD	mN	>150	Tappi T494
Tensile strenght	MD	N/inch	>200	Tappi T494
	CD	N/inch	>120	Tappi T494
Elongation	MD	%	> 5	Tappi T494
	CD	%	> 7	Tappi T494
Fold resistance	MD	DF	>12000	Tappi T423
	CD	DF	>6000	Tappi T423
Changes	Date of issue		04.10.2021	
	Revision state		02	

date/signature  
 supplier

.....

date/signature  
 customer

.....

Issued 07.11.2016